WEDOLIT AN 6723

Special-Fluid 100°C flash point

(aromatic content ≤ 2%)

WEDOLIT AN 6723 is a thixotropic corrosion protection oil for steel. It contains a combination of inhibitors which offers long-term protection for indoor storage and short-term protection for outdoor storage. It can be applied by spraying, flooding, brushing or rolling.

WEDOLIT AN 6723 fulfills all requirements regarding Altautorichtlinie 2000/53/EG. It is not subject to the German VOC-regulation (VOC-guideline, 31. BlmSchV) nor to the Swiss regulation for VOC (Lenkungsabgabe VOCV Swiss).



Physical Properties Typical Data

Parameter	Typical results	Tested according to
Appearance:	Medium-brown, turbid, pasty	Visual
Density at 15°C:	0.90 g/cm ³	ASTM D 7042
Viscosity at 20°C:	Not measurable	ASTM D 7042
Flash point:	> 100 °C	DIN EN ISO 2719
Film weight:	Depending on the application	Dipping procedure
Film type:	Waxy	Haptical
Dewatering effect:	None	Internal test method
Water separation:	None	Internal test method
Humidity test:	1800 cycles	DIN EN ISO 6270-2 AHT
Salt spray performance:	36 h	DIN EN ISO 9227 NSS

Application Guidelines

Storage must be frost-free between 5 - 35°C.

The minimum durability is 12 months in an original sealed package.

Additional Information

The information herein is given in good faith and believed current as of the date of publication and should apply to the current formula version. Because conditions of use are beyond our control, no guarantee, representation, or warranty expressed or implied is made. Consult Master Fluid Solutions for further information. For the most recent version of this document, please go to this URL: https://2trim.us/diw/?plr=AN-6723*en*eu

WEDOLIT AN 6723

©2019-2020 Master Fluid Solutions $^{\text{\tiny{M}}}$ | 2020-08-12





Choose WEDOLIT AN 6723:

- · Ideal for overseas transport
- Stable against acidic and alkaline impurities
- · Good material compatibility
- The full corrosion protection develops, if the product is applied at temperatures of 50 - 60°C (for spraying: The temperature has to be adapted according to the specifications of the used device)
- For an optimal protection of the treated parts, storage temperatures
 ≥ 36°C and a direct exposure to solar radiation should be avoided

Health and Safety

For further information, see the most recent SDS which is available directly from Master Fluid Solutions.

Hasselsstraße 6-14
Düsseldorf, 40597
Germany



+49 211 77 92 85 - 0



info-eu@masterfluidsolutions.com



masterfluidsolutions.com/eu/en/